

# Mooring Line Certificate

Demonstrates that the product has been manufactured, tested & documented following the guidelines in appendix B of the *Mooring Equipment Guidelines, Fourth Edition*.

**Name & Address of Manufacturer** : Kohinoor Ropes Pvt. Ltd. Selu-431 503 Dist. Parbhani, Maharashtra, India

**Line Standard** : Manufactured according to ISO 10556:2010 &  
Tested according to ISO 2307:2019

## Line supply information

Ship design MBL	-	Certificate No.	KRPL/22/06/2222440109/01
NSBF	93.5 M Tons	Date	29-06-2022
Size	68 mm.	Coil No.	206,210,212
Length	220 mtr		
Jacketed	No		
Splice type and design	Eye (Six Tucks)		
Material type and grade	Polypropylene & Polyester		
Line design designation (product name)	TECHFLEX		
Line construction	8-Strand Braided		
Rotating	Yes		

## Performance Indicators

Line Design Break Force (LDBF)	92.10 Tons
Line Linear Density (LLD)	2540 gm/m
Load Bearing Linear Density (LBLD)	2540 gm/m

	Measured	Maximum
Line Tenacity (LT)	0.0362 Tons / (gm/m)	0.0362 Tons / (gm/m)
	D/d Ratio:5	D/d Ratio:10
Angled Break Force*(ABF) % Avg NSBF	185.99	200.41
Angled Endurance*(AE) % Avg NSBF	76.67	75.13

	-20° C	0° C	20° C	40° C	60° C	80° C
Temperature (T) % BF at 20° C for PP	100.49	100.06	100.00	99.54	99.42	98.60
Temperature (T) % BF at 20° C for PES	101.31	100.63	100.00	98.68	98.55	98.24

Axial Compression Resistance*(ACR)	112.27 % Avg NSBF
------------------------------------	-------------------

	%LDBF:10	%LDBF:20	%LDBF:30	%LDBF:40	%LDBF:50
Average Immediate Strain* (e)	6.49	7.59	8.69	9.74	10.78

## Line Description

8 Strand TECHFLEX Rope, White Color, With 1.8 mtr Eye-Splicing Wrapped With Canvas At Both Ends, UV Resistant.




QC Incharge